Primary lithium batteries LS 14250C

3.6V Primary lithium-thionyl chloride (Li-SOCl₂)
High energy density
½ AA-size bobbin cell
(recommended for cool temperature environments)

Preferably for moderate temperature uses (i.e. indoor applications with occasional T excursions up to $+55\,^{\circ}\text{C}$), requesting superior voltage response and operating life.



Key features

- High and stable operating voltage
- Superior voltage response during pulsing at ambient T
- Low self-discharge rate (less than 1% after 1 year of storage at +20°C)
- Stainless steel container and end caps (low magnetic signature)
- Hermetic glass-to-metal sealing
- Non-flammable electrolyte
- Compliant with IEC 86-4 safety standard and EN 50020 intrinsic safety standard
- Underwriters Laboratories (UL)
 Component Recognition
 (File Number MH 12609)
- Non-restricted for transport

Main applications

- Utility metering
- Alarms and security devices
- Memory back-up
- Computer real-time clocks
- Tracking systems
- Professional electronics

etc...

	1 1
Cell size references	½ UM3 - ½ R6 - ½ AA
Electrical characteristics	
(typical values relative to cells stored for one year or less at + 30°C	max.)
Nominal capacity (at 1.5 mA + 20°C 2.0V cut off. The capacity restored by the cell via according to current drain, temperature and cut off).	1.20 Ah aries
Open circuit voltage (at + 20°C)	3.67V
Nominal voltage (at 0.1 mA + 20°C)	3.6V
Pulse capability: Typically up to 50 mA (50 mA/0.1 second pulses, drained every 2 mn at $+20^{\circ}\mathrm{C}$ from undischarged cells with 10 $\mu\mathrm{A}$ b current, yield voltage readings above 3.0V. The readings may vary at to the pulse characteristics, the temperature, and the cell's previous Fitting the cell with a capacitor may be recommended in severe cond Consult Saft)	ccording s history.
Continuous current permitting 50% of the nominal capacity	


to be achieved	rrent permitting 50% of the nominal capacity at + 20°C with 2.0V cut off. ts possible, consult Saft)	15 mA
Storage	(recommended) (for more severe conditions, consult Saft)	+ 30°C (+ 86°F) max
Operating temperature range		-60°C/+55°C
(Operation above ambient T may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult Saft)		(- 76°F/+131°F)

Physical characteristics


Diameter (max)	14.65 mm (0.58 in)
Height (max)	24.8 mm (0.98 in)
Typical weight 8.9 g (0.3	
metal content approx. 0.3 g	
Available termination suffix	
CN, CNR	radial tabs
2 PF, 3 PF, 3 PF RP, 4	F radial pins
CNA (AX)	axial leads
FL	flying leadsetc.




LS 14250C



Dimensions in mm.



Voltage plateau versus Current and Temperature (at mid-discharge)




Typical discharge profiles at +20°C

Storage

The storage area should be clean, cool (not exceeding + 30°C), dry and ventilated.

Warning

- Fire, explosion and severe burn hazard.
- · Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell.



Restored Capacity versus Current and Temperature (2.0V cut off)

Saft

12, rue Sadi Carnot 93170 Bagnolet - France Tel +33 1 49 93 19 18 Fax +33 1 49 93 19 69

www.saftbatteries.com

Doc. No 31010-2-0904 Published by the Communications Department

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft. For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2-0604.

Photo credit: Saft Produced by Arthur Associates

Société anonyme au capital de 31 944 000€ RCS Bobigny B 383 703 873

